
植物由来の銀面調人工皮革 Ultrasuede® nu

Plant-based Ultrasuede® nu



東レは植物由来の再生資源を粗原料の一部に使用した Toray started commercial production of its non-woven スエード調人工皮革を、2015年に世界で初めて商業生産開始。 Ultrasuede®は「責任ある製品づくり」を通してカーボン ニュートラル社会実現に加え、原料そのものを変えること で脱石油依存に向けて貢献したいと考えています。 また使用される植物由来原料は供給と品質が安定し、 信頼性もある事から、より地球と人に配慮した持続可能 な素材だと考えています。

植物由来素材*のメリット

- ・脱石油依存社会への貢献
- ・安心できる供給と品質
- · 原料の信頼性 (不可食部、非GMO、試験証明)

material with a suede texture, which uses recycled resources derived from plants as part of its raw materials, for the first

Through Ultrasuede®, Toray helps to realize a carbon-neutral society by employing a chemcal recycling system as well as by sourcing its raw materials from plant-based polymers. This provides the advantage of stable supply, quality and reliability. We consider these sustainable materials to be better for the Earth and its people as we aim to build a sustainable society through responsible manufacturing.

'TORAY'

The advantages of plant-based materials*

- Contribute to a non-oil-dependent society
- Secure supply and stable quality
 Reliable as raw feedstocks
- (non-edible part, non-GMO, test certification)

ultrasuede nu

問い合わせ先:

東レ株式会社 ウルトラスエード事業部

大阪市北区中之島3-3-3 06-7688-3373

東京都中央区日本橋室町2-1-1 03-3245-5401

For inquiries, please visit: ultrasuede.com/contact

You may also contact our regional office directly:





www.toray.com

www.ultrasuede.com

NORTH AMERICA Toray International America Inc. Ultrasuede Department 1251Sixth Avenue, Suite 930, New York, NY 10020 +1-212-697-8150 for product information and new accounts 1-800-633-8870 for existing customers within North America

EUROPE

Toray International Europe GmbH Frankfurt am Main +49-6102-7999 Ext. 121 & 128

Toray International (China) Co.,Ltd. Shanghai +86-21-3251-8553 Ext.4214

JAPAN, KOREA, ASIA AND OTHER PARTS OF THE WORLD Toray Industries, Inc.

Osaka +81-6-7688-3373 Tokyo +81-3-3245-5401

Innovation by Chemistry.

素材には、社会を変える力がある。

東レグループは、「全ての製品の元となる素材には、社会を本質的 に変える力がある」という強い信念のもと、「先端材料で世界の トップ企業を目指す」総合化学企業集団です。創業以来、「社会へ の奉仕」を存立の基礎とし、企業理念である「わたしたちは新しい 価値の創造を通じて社会に貢献します」のもと、革新技術・先端材料 の提供を通じて、全世界のパートナーとともに世界的課題の解決 の加速に挑戦しています。そして、全てのステークホルダーにとって 高い存在価値のある企業グループを目指しています。

Innovation by Chemistry.

Materials can change our lives.

Toray Group firmly believes that "materials, as the foundation of all products, have the power to bring about fundamental transformations in society." Based on this belief, our goal is to become a global top company in advanced materials as an integrated chemical industry group. Since our establishment, we have positioned "contributing to society" as the focus of our existence. Carrying this focus into our corporate philosophy of "contributing to society through the creation of new value with innovative ideas, technologies, and products," we are ramping up efforts to solve a host of issues worldwide together with global partners by providing innovative technologies and advanced materials. With this in mind, we are working to become a corporate group that provides high value to all stakeholders.

ultrasuede nu

Style: 3894

ウルトラスエード®ヌーは、豊かな質感や意匠性、高い機能性を兼ね備 えた銀面調人工皮革です。

1970年、東レは世界初の海島型極細繊維技術による不織布構造の画 期的な素材を開発。

以来積み重ねてきた技術をもとに、ジャパン・クオリティの素材として これまでに無い新たな選択肢を提供します。

Ultrasuede®は、未来の「美しき可能性」に向けて進化する素材です。

仕様

品	番:	3894
規	格:	1,300mm×30m 乱
目	付:	230±20g/㎡
厚	さ:	0.6±0.1mm
繊維	径:	0.04dtex

組 成: 約44% ポリエステル:極細繊維(約31% 植物由来) 約36% ポリエステル:スクリム(約18% 植物由来) 約20% ポリウレタン(約31%植物由来)(国内表示:人工皮革)

Ultrasuede®nu is a non-woven material created using ultra-fine fibers having a genuine grain leather appearance. It features a luxurious texture with advanced functionality and offers creative design possibilities. In 1970, Toray developed an innovative product: the world's first non-woven

material created using ultra-fine fibers in our "Island in the Sea" configuration. Based on all the technological expertise the company has accumulated since then, the debut of Ultrasuede®nu marks a superlative new option for optimum quality material from Japan.

Ultrasuede® keeps evolving toward a future full of "Beautiful Possibilities."

SFECII ICATIONS
Style: 3894
Width: 51" / 1,300mm
Put-up: 33 yard / 30m R.O.T.
Weight: Approx. 6.8±0.7 oz. per sq. yard / 230g±20 per sq. meter
Thickness: 0.6±0.1mm
Fiber Fineness: 0.21 dtex
Composition: 44% Polyester non-woven (approx. 31% plant-based PET); 36% Polyester woven scrim (approx. 18% plant-based PET) 20% Polyurethane non-fibrous binder (approx. 31% plant-based PU)



DE1 Garnet DC2 Carbon Gray

GB2 Black GB7 Navy

WA7 Blue

Ultrasuede® nu 0.6

きめ細かく滑らかな風合いと銀面調の豊かな艶、 高い機能性を兼ね備えたストレッチタイプ「0.6mm」

■銀面調の光沢とスエードタッチを兼ね備えた繊細な質感

- ■美しい発色、多彩なカラーバリエーション
- ■優れた堅牢度
- ■適度な通気性
- ■お手入が簡単な高いメンテナンス性
- ■裁ち切りや後加工が自由自在の意匠性
- ヴィーガン (非動物性) 素材

素材お取り扱い上の注意点

- ウルトラスエード®ヌーは他の素材の白や淡色とウルトラス エード®ヌーの中濃色の組合せは色移りの恐れがありますの で、予め十分ご注意下さい。
- 本商品は、生地表面に特殊な樹脂加工を施しており、微細か つランダムな柄感を有した点も本素材の特徴となっておりま すが、短尺ではその表現が見えづらいかも長尺での品位確認 をお願いします。また、生地表面の特殊な樹脂は大変デリケートなため、生地の加工および取り扱いにおける擦れなど で部分的に白く見えることがありますが、安全上の問題はご
- 本商品は、色相、光沢感及びタッチ感について、反内、ロット 間で多少の差異が生じる可能性があります。

お手入れ方法

- 洗濯は、石油系のドライクリーニングをおすすめします。
- ・ 非常にデリケートな素材ですので、液温30℃以下にて、軽く 押し洗いをして下さい。なお、物理的衝撃(擦る、捻るなど) を与えますと、表面感が変化する恐れがありますので、ご注意 下さい。
- 他素材の商品と一緒に洗うことはお避け下さい (素材、色相によっては、汚染する可能性があります)。
- 洗剤を使用する場合は、液体中性洗剤のご使用をおすすめし ます。塩素系漂白は使用しないでください。
- アイロンは低温 (110℃以下) で、布目の目立たない当て布をし てください。強く押したり、一カ所に静止しないように軽くア イロンがけして下さい。
- ウルトラスエード®ヌーは非常に細い繊維で構成され、かつそ の表面は、特殊処理されたソフトな 風合いの銀面調人工皮革 です。頻繁に自転車に乗ったり、バッグ等で同じ部分だけ繰り 返し擦られると、光沢感の変化、毛羽立ち、擦り切れの原因と なることがありますのでご注意ください。
- 保管は袋に入れて直射日光、高温、多湿な場所は避けてくだ さい。

取扱絵表示 🎬 🕸 🗵 🗗 🔁 🕟 😿

品質(物性・染色堅牢度)

ピリング(級) JIS L1076 A (ICI型試験機10時間) ≥ 3級 摩擦強さ(回) JIS L1076 E 法(マーチンデール法2万回、 ≥ 3級 毛羽立ち社内基準) 洗濯寸法変化率(%) AATCC96-1998(1-C) 家庭用電気洗濯機40°C×30分			
ピリング(級) JIS L1076 A (ICI型試験機10時間) ≥ 3級 摩擦強さ(回) JIS L1076 E 法(マーチンデール法2万回、 ≥ 3級 毛羽立ち社内基準) 洗濯寸法変化率(%) AATCC96-1998(1-C) 家庭用電気洗濯機40°C×30分	引裂強力(N)	JIS L1096 D法(ペンジュラム法)	≧ 7N
摩擦強さ(回) JIS L1076 E法(マーチンデール法2万回、 ≥ 3級 毛羽立ち社内基準)	引張強力(N/cm)	JIS L1096 A準拠(カットストリップ法)	≧ 200N
 毛羽立ち社内基準) ニ羽立ち社内基準) 洗濯寸法変化率(%) AATCC96-1998(1-C) 家庭用電気洗濯機40°C×30分 摩擦堅牢度(級) JIS L0849(学振法) 競操 湿潤 湿潤 証潤 シと4級 洗濯堅牢度(級) AATCC-61-1986 1-A法 変退色 汚染 昇華堅牢度(級) JIS L0846 変退色 汚染 昇華堅牢度(級) JIS L0854 準拠 変退色 変退色 汚染 	ピリング(級)	JIS L1076 A(ICI型試験機10時間)	≧ 3級
家庭用電気洗濯機40°C×30分 -3%~+ 常標 Span を	摩擦強さ(回)		≧ 3級
湿潤≧ 耐光堅牢度(級) JIS L0842 (カーボンアーク) ≥ 4級 洗濯堅牢度(級) AATCC-61-1986 1-A法 変退色 汚染 汗堅牢度(級) JIS L0846 変退色 汚染 昇華堅牢度(級) JIS L0854 準拠 変退色	洗濯寸法変化率(%)		-3%~+1%
洗濯堅牢度(級) AATCC-61-1986 1-A法 変退色 污染 汗堅牢度(級) JIS L0846 変退色 污染 昇華堅牢度(級) JIS L0854 準拠 変退色	摩擦堅牢度(級)	JIS L0849(学振法)	乾燥 ≧4級 湿潤 ≧3級
污染 汗堅牢度(級) JIS L0846 変退色 污染 昇華堅牢度(級) JIS L0854 準拠 変退色	耐光堅牢度(級)	JIS L0842 (カーボンアーク)	≧4級
	洗濯堅牢度(級)	AATCC-61-1986 1-A法	変退色 ≥ 4.6 汚染 ≥ 3.6
	汗堅牢度(級)	JIS L0846	変退色 ≧ 4 ⁄ 汚染 ≧ 3 ⁄
乃未	昇華堅牢度(級)	JIS L0854 準拠	変退色 ≥ 4 % 汚染 ≥ 3 %

※上記に記載されている品質は当社出荷時の参考値であり 保証値ではございませんのでご了承ください。 ※特濃色の堅牢度につきましては別途お問い合せください。 0.6mm-thick stretch type with a delicate texture, smooth touch and grain leather-like luster plus high functionality

- Refined, delicate texture combines grain-side leather's
- lustrous shine with smooth hand ■ A wide range of exquisite colors
- Breathability for true comfort

- Easy maintenance
 It's both uniform and lightweight, easily processed for a multitude of products and uses
 Unlimited creative options such as laser cutting,
- embossing and printing ■ Vegan (non-animal) material

NOTES FOR HANDLING

- When combining medium/dark-colored Ultrasuede®nu with lighter-colored materials, color migration may occur.
- Ultrasuede®nu fabric surface is specially finished with resin that produces delicate and random patterns on the surface. This unique pattern might not be noticed on a short piece of fabric, so please perform your quality check on a long fabric piece. In addition, the surface is extremely delicate that you might see white dots partially due to rubbing, but this is not a safety issue.
- Ultrasuede®nu may have slight differences in color, luster, and/or touch within a fabric roll or between fabric lots.

CARE INSTRUCTIONS

- Dry cleanable by conventional method.
- Because Ultrasuede®nu is an extremely delicate material, handwash by gently pushing it down in a liquid at below 30°C. Avoid rubbing or twisting as it may deteriorate Ultrasuede®nu's surface texture
- An Ultrasuede®nu product should not be washed together with other items, as color migration may occur depending on the material or color of other items.
- When using a detergent, liquid neutral detergent is recommended. Do not use chlorine bleach.
- When ironing, use a low temperature setting (110°C or lower) and place a seamless cloth on top of the product. Use light pressure and never press the iron too hard or stop at one place on the product.
- Ultrasuede®nu is a non-woven material made of ultra-fine fibers having a specially treated soft feel and a genuine grain leather appearance. As such, repeated rubbing may alter its lustrous appearance or cause excessive fuzzing or fabric tears.
- When storing, place the Ultrasuede®nu product in a bag. Avoid storing in places subject to high temperature or high humidity.

Quality Specification (Physical Properties and Colorfastness)

CHARACTERISTICS	METHOD	Specification
Tear Strength (N)	ISO 13937-1	≧7N
Tensile Strength (N)	ISO 13934-1	≧200N
Pilling Resistance (Grage)	ISO 12945-1 (10 hours)	≧Grade3
Abrasion Resistance (Grade)	ISO 12947-2(12KPa) Change in Apperance(Internal Standard)	≧Grade3
Dimensional Change after Washing (%)	ISO 6330 4M-C (Front Loading Washing Machine/3 times)	-3%to+1%
Colorfastness to Rubbing (Grade)	ISO 105-X12	Dry ≧Grade4 Wet ≧Grade3
Colorfastness to Light (Grade)	ISO 105-B02 (Xenon)	≧Grade3
Colorfastness to Perspiration (Grade)	ISO 105-E04	Color Change ≧Grade4 Staining ≧Grade3
Colorfastness to Washing (Grade)	ISO 105-C06 B2S	Color Change ≧Grade4 Staining ≧Grade3